




## HDPE HM9450F (EX5)









## **MAIN APPLICATIONS:**

FOR BLOWN FILMS WITH PAPERLIKE QUALITY, SUITABLE FOR COUNTER BAGS, CARRIER BAGS AND WRAPPING FILMS EXCELLENT PROCESSING

Test/Composition	Typical Value	Unit	ASTM Method
Density	0.949	g/cm3	ISO1183
Fish Eye Note	<3	note	Internal
FRR (21.6/5)	29	h	-
MFR 190°/21.6	8.0	g/10min	ISO1133
MFR190°/5	0.28	g/10min	ISO1133

